

General PMMA ACRYREX® CM-207

产品叙述: Medium viscosity

物性	ISO 测试方法	测试条件	单位	CM-207
熔融指数	1133	230°C×3.8KG	ml/10 min	8.5
比重	1183	23 °C	g/cm ³	1.19
拉伸强度	527	5 mm/min, yield	MPa	67
		5 mm/min, break	MPa	67
延伸率	527	5 mm/min	%	8
弯曲强度	178	2 mm/min	MPa	97
弯曲弹性模数		2 mm/min	GPa	2.7
IZOD 冲击强度	180/1A	23°C, Notched	KJ/m ²	2
		-30°C, Notched	KJ/m ²	—
Charpy 冲击强度	179	23°C, Notched	KJ/m ²	2
		-30°C, Notched	KJ/m ²	—
维氏软化温度	306	50°C/hr;1KG	°C	107
		50°C/hr;5KG	°C	99
热变形温度	75/A	1.8MPa, unannealed	°C	80
		1.8MPa, annealed	°C	97
线膨胀系数	11359	-	-	6 X 10 ⁻⁵
燃烧等级	-	UL-94	-	1.5mm HB
成型收缩率	294-4	-	%	0.2~0.6
标记	1043	-	-	>PMMA<

June 27, 2025

Notes: The value provided herein has been established on above test methods and conditions, which only as reference for selecting material, NOT guaranteed values or formal specifications. There can be variation within normal tolerances in colors.

All information contained herein are typical values for reference and CHIMEI CORPORATION ("CHIMEI") reserves the right to revise it without notice. The information correspond to our best knowledge as of the date of publication and stated in lieu of all other warranties and statements, whether express, statutory, or implied. Each user shall bear full responsibility for making its own determination as to the suitability of our materials, products, services or recommendations for its own particular use. In no event will CHIMEI be liable for any indirect, special, exemplary, punitive or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling or use of any product or otherwise.

Any information revealed herein is owned by CHIMEI or legally authorized by the rights holders, and protected by any and all domestic or foreign copyright, intellectual property laws. Nothing herein shall be deemed as any patent, copyright, trademark, or license in the information is granted or implied for any use.